

Part Number DWHST-HWA

Header DWHST-HWA Heavy Wall Polyolefin Heat Shrink Tubing With Adhesive Liner

Description Thermosleeve-USA DWHST-HWA heavy wall heat shrink tubing with adhesive liner provides exceptional reliability and offers rugged resistance to impact and abrasion. DWHST-HWA tubing protects against the most extreme weather conditions and is resistant to acids and alkalis. When heated, the internal adhesive flows to form a positive seal creating an excellent barrier against moisture. Especially designed for reliable performance, DWHST-HWA tubing is manufactured to cover a broader range of applications in fewer sizes *due to its bigger* shrink ratios. DWHST-HWA has a minimum shrink temperature rating of 120 degrees C (248 degrees F). DWHST-HWA is also available without adhesive liner...see Thermosleeve part number HWT

Agency Approval & Compliance ROHS, Halogen free, SAE, Flame Retardant, UL224, REACH, VW1

Application DWHST-HWA heat shrink tubing with adhesive liner is designed to seal and protect components and electrical splices from moisture and corrosion. Widely used to provide insulation and strain relief cover to both wire terminations and electrical connectors, the adhesive liner bonds to a wide variety of materials including plastics, rubbers and metals. DWHST-HWA shrinks quickly, requires no special skills and is easy to use.

Shrink Ratio and Operating Temperature DWHST-HWA shrink ratios range between 3:1 and 4:1...please consult the Thermosleeve website for specific sizes and shrink ratios. The tubing's wall thickness will also change proportionally to the degree of recovery.

DWHST-HWA has a continuous operating temperature rating of -55 degrees C (-67 degrees F) and 110 degrees C (230 degrees F)

Standard Sizes and Dimension



Size	As Supplied (mm)		After Recovery (mm)	
	Inside Diameter (D)	Wall-thickness (T)	Inside Diameter (d)	Wall-thickness (t)
Φ9	≥9.0		≤3.0	≥2.0
Φ13	≥13.0		≤4.0	≥2.4
Φ16	≥16.0		≤5.0	≥2.5
Φ19	≥19.0		≤5.0	≥2.5
Φ22	≥22.0		≤6.0	≥2.7
Φ33	≥33.0		≤8.0	≥3.2
Φ40	≥40.0		≤12.0	≥4.0
Φ45	≥45.0		≤12.0	≥4.0
Φ55	≥55.0		≤16.0	≥4.0
Φ65	≥65.0		≤19.0	≥4.0
Φ75	≥75.0		≤22.0	≥4.0
Φ80	≥80.0		≤22.0	≥4.0
Φ85	≥85.0		≤25.0	≥4.2
Φ95	≥95.0		≤30.0	≥4.2
Φ105	≥105.0		≤30.0	≥4.2
Φ115	≥115.0		≤34.0	≥4.2

Φ130	≥130.0		≤36.0	≥4.2
Φ140	≥140.0		≤37.0	≥4.2
Φ160	≥160.0		≤50.0	≥4.2
Φ180	≥180.0		≤50.0	≥4.2
Φ200	≥200.0		≤60.0	≥4.2

Typical Properties

Property	Specification
Operating Temperature (°C)	-55 ~ 125
Tensile strength	14.5 MPa
Ultimate Elongation (%)	≥450
Tensile Strength (MPa) - After Aging	13.5
Ultimate Elongation (%) - After Aging	400
Density	
Concentricity	70
Longitudinal shrinkage	5
Dielectric strength	≥21kV/mm
Cracking Resistance	No cracking
Adhesive	
Water absorptivity	0.15%
Softening Point	85°C
Peel Strength (N/25mm)	8
Copper stability	Pass
Antibacterial Property	Pass

Availability Four-foot lengths and cut pieces

Important Notice The information related to Thermosleeve-USA products both in printed or electronic format is believed to be reliable but the accuracy and completeness is not guaranteed. We suggest that before using this product, you evaluate and determine if it is suitable to your intended application. Thermosleeve-USA assumes no risk or liability associated with the use of this material. Any statements related to this product that are not contained in the current Thermosleeve-USA online or printed literature, or any contrary statements referenced on purchase order, shall have no force or effect unless expressly agreed to in writing and signed by an office of Thermosleeve-USA.

Limited Warranty/Limited Liability Thermosleeve-USA offers no guarantees in respect to the accuracy of the information detailed in this document and accepts no explicit or applied liability as to the products use. In no instance will Thermosleeve-USA be liable for any eventual, indirect or consequential damage or damages arising from the sale, resale, transfer, use or misuse of the product. Thermosleeve-USA specifications are subject to change without notice; including changes in materials and processing that do not affect compliance of the products specification. Thermosleeve-USA guarantees the product to be free from defects in material and manufacturing at the time of purchase. If this product is found to be defective within the warranty period, at our option we will refund the purchase price, replace or repair the Thermosleeve-USA product.